

## **Commercial Solutions Division** 3M<sup>™</sup> Scotchcal<sup>™</sup> Graphic Film Series 5525C SE 3M<sup>™</sup> Scotchcal<sup>™</sup> Graphic Film Series 5525 SE

3M™ Scotchcal™ Graphic Film Series 5525C SE and 3M™ Scotchcal™ Graphic Film Series 5525C SE are Product designed for medium term window and backlit applications. Description Product variants with Comply<sup>™</sup> adhesive also have air release channels for fast and easy, bubble-free graphic installations. Product Line Window decoration 5525 SE-324 sandblast finish, translucent, matte, removable adhesive. 55525C SE-324 sandblast finish, translucent, matte, removable adhesive with Comply™. 5525 SE-314 haze finish, translucent, matte, removable adhesive. 5525C SE-314 haze finish, translucent, matte, removable adhesive with Comply™.

## Product

These are indicative values for unprocessed products. Contact your 3M representative for a custom specification.

<b>Characteristics</b>
Physical & Application

n	Material	calendered vinyl (polymeric)					
	Surface finish	matte					
	Thickness (film)	80 µm (0.08 mm)					
	Adhesive type	solvent acrylic, pressure-sensitive					
		Comply™ adhesive have air release channels					
	Adhesive appearance	clear					
Liner Kraft paper							
		versions with Comply:		double-sided Polyethylene coated paper			
	Adhesion	approx. 12 N/25 mm		FTM 1: 180° peel, substrate: glass; cond: 24 h 23°C/50%RH			
	Application method	wet or dry					
		versions with Comply:		dry only!			
	Applied shrinkage	< 0.4 mm	FTM 14				
	Application temperature (minimum air and substrate)	+10°C	for flat surfaces				
	Service temperature (after application)	-40°C to +80°C	(not for extended periods of time at the extremes)				
	Surface type	flat					
	Substrate type	glass, PMMA, PC*, PETG*, ABS *Might require drying with heat before use					
	Graphic removal Hard to remove from supported substrates.						
	The values above are the results of illustrative lab test measurements and shall not be considered as a						

The values above are the results of illustrative lab test measurements and shall not be considered as a commitment from 3M.

Storage	Shelf life	Use within two years from the date of manufacture on the sealed original box. Use within one year after opening the box.				
	Storage conditions	+4°C to +	40°C, out of sunlight, c	of sunlight, original container in clean and dry area.		
	The shelf life as defined ab controllable factors. It may	subject to many external and non-				
Flammability	7 DIN 4102 Part 1 - Fire Behavior of Building Materials and Building Components - Building Materials, Requirements and Tests. Achieved level: B1.					
Durability	<ul> <li>The durabilities mentioned in the table below are the results of illustrative lab tests. The values show the best performance expected from these products, provided that the film will be processed and applied professionally according to 3M's recommendations. The durability statements do not constitute warranties of quality, life and characteristics. The durability of products is also influenced by:</li> <li>the type of substrate and thorough preparation of the surface (with 3M™ Surface Preparation System)</li> <li>application procedures</li> <li>environmental factors</li> <li>the method and the frequency of cleaning</li> </ul>					
	Unprocessed film	. ,	ving durability data are	aivon for un	processed film only!	
	onprocessed min	The follow		given for an	processed min only:	
	Climatic zones	s Graphic durability is largely determined by the climate and the angle of exposure. Find below a table showing the durability of a product according to the angle of exposure and the geographical location of the application.				
		Zone 1	Northern Europe, Ital	y (north of F	Rome), Russia	
		Zone 2	Mediterranean area v	without Nort	h Africa, South Africa	
		Zone 3	Gulf area, Africa			
	Exposure types	Vertical:	face of graphics	The face o ±10° from	f the graphic is vertical.	
		Interior:	Interior means an app exposure to sunlight.		de a building without direct	
	Vertical outdoor exposure	Zone 1	Zone	2	Zone 3	
	transparent	4 years	3 years		2 years	
	Interior application	Zone 1	I Zone	2	Zone 3	
	interior	5 years	5 years		5 years	
	3M™ Performance Guarantee and MCS™ Warranty	ntee and MCS <sup>™</sup> within the framework of 3M <sup>™</sup> Performance Guarantee and/or 3M <sup>™</sup> M				
Limitations of End Uses Graphics applied to	3M specifically does not reneeds to recommend othe	r products.			lease contact us to discuss your ubstrate.	

- flexible substrates incl. 3M<sup>™</sup> Panagraphics<sup>™</sup> III Wide Width Flexible Substrate.
- low surface energy substrates or substrates with low surface energy coating.
- other than flat surfaces.
- painted or unpainted rough wallboards, gypsum boards and wallpapers.
- stainless steel.
- substrates with tendency of outgassing.
- surfaces that are not clean and smooth.

- Graphic removal from - signs or existing graphics that must remain intact. Graphics subjected to - gasoline vapors or spills. Important Notice - 3M Commercial Solutions products are not tested against automotive manufacturer specifications! - Application between two sheets of glass is not recommended! - Versions with Comply<sup>™</sup> are not suitable for electrocut graphics! - To avoid color variations all pieces of applied film of one colored area should be processed out of one lot of material. Spectral tau value. According to DIN 5033, part 3 and 7; Ultascan XE, light source diffuse/8°, observer 10°, Special D65 Information Typical values for unprocessed product. Not for use in custom specification! Translucency values SC5525 SE-314 87% ± 2% SC5525 SE-324 69% ± 2% SC5525C SE-314 81% ± 2% SC5525C SE-324 73% ± 2%
  - Piezo Ink Jet All variants of films series 5525 SE are piezo inkjet printable. The graphics manufacturer must test, approve and accept all responsibility for satisfactory use.

## Graphics Manufacturing

Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

Shipping finished graphics

Converting Information	Based upon cutting evaluations the minimum height for text is 25 mm using upper and lowercase Helvetica Medium. The stroke width should not be lower than 1 mm.
Electronic Cutting	The variable characteristics of electronically controlled cutting equipment require users to verify their specific requirements.
Sharpness of knife blade	Dull blades impart a serrated look to the edge of the cut film.
Weight of knife blade	The ideal weight slightly scores the liner. Too little weight does not cut completely through the film and the adhesive. Excessive weight cuts the liner and causes the blade to drag, accelerating wear and creating a serrated cut edge on the film.
Weeding	The excess film should be weed (removed) as soon after cutting as practical. This is to minimize the effect of possible adhesive flow.
•	Temperature and relative humidity are minor considerations, but avoid extreme or rapid fluctuating conditions.
Roll storage	Store the film in the same environment as the cutting equipment.
Further information	For more details refer to our instruction bulletin 4.1 'Sheeting, Scoring, Film Cutting', please.
	>Instruction Bulletin 4.1'Sheeting, Scoring, Film cutting'<
Application	See product bulletin ATR 'application tape recommendations' for information about selection and use of suitable application tapes for this product, please.
	> Product Bulletin Application Tape Recommendations <
	Refer to Instruction Bulletin 5.1 'select and prepare substrates for graphic application', for general application information.
	>Instruction Bulletin 5.1 'select and prepare substrates for graphic application'
Maintenance and Cleaning	Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline).
-	Refer to Instruction Bulletin 6.5 'storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.
	>Instruction Bulletin 6.5 'Storage, Handling, Maintenance and Removal of Films and Sheetings'

## Important Safety Remark

Application to glass

The application of colored or printed film onto glass with sunlight exposure can lead to glass breakage through thermal expansion of the glass. The local conditions must be examined for the danger of glass break by uneven heat absorption through sun exposure. Type of glass (insulation glass, float glass, LSG, toughened safety glass, semi-tempered glass, etc.), glass dimension, joint condition, flexibility of the sealant, quality of the edge finishing, geographical orientation and partial shadow during sun exposure are the determining factors. Light color designs and application on the outside of the window are to be preferred. A free non-applied framework of 4 mm around the entire window front can help to dissipate the absorbed warmth. According to common knowledge a thermal crack can occur at temperature differences of approx. 130°C (toughened safety glass), approx. 40°C (float glass) or approx. 110°C (semi-tempered glass). Coldest place is usually under the framework in the embedded joined window part, the warmest place is typically on the darkest place in the format. Because of the many above mentioned factors, glass breakage cannot be fully predicted, therefore 3M does not accept liability for glass breakage when using this film for window graphics.

Remarks	This bulletin provides technical information only.						
Important notice	All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.						
	Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.						
	As outdoor graphics age, natural weathering occurs causing a gradual reduction in gloss, slight color changes, some lifting of the graphic at the edges or around rivets, and ultimately a minor amount of cracking.						
	These changes are not evidence of product failure and are not covered by a 3M warranty.						
Additional information	Visit the web site of your local subsidiary at <u>www.3Mgraphics.com</u> for getting:						
	<ul> <li>more details about 3M<sup>™</sup> MCS<sup>™</sup> Warranty and 3M<sup>™</sup> Performance Guarantee</li> <li>additional instruction bulletins</li> </ul>						
	- a complete product overview about materials 3M is offering						
	Responsible for this technical bulletin 3M Controltac Envision Scotchcal Comply MCS and						



**Commercial Solutions Division** Hermeslaan 7 1831 Diegem, Belgium Responsible for this technical bulletin

3M Deutschland GmbH Carl-Schurz-Str. 1 41453 Neuss, Germany 3M, Controltac, Envision, Scotchcal, Comply, MCS, and Panagraphics are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.