

TITAN ELECTRIC RED | TERX-140

High tack fluorescent red print vinyl with micro channel liner developed to create outstanding graphics on powervehicles.

FACE FILM

PVC, fluorescent red

| | | |
|---------------------------------------|-----|----------------|
| Thickness (µm) | 140 | |
| Tensile strength (N/mm ²) | 11 | EN ISO 527-3 |
| Elongation at break (%) | 150 | DIN EN ISO 527 |

ADHESIVE

Clear solvent-based acrylic, high tack permanent

| | | |
|--------------------------|----|-------------|
| Thickness (µm) | 70 | |
| Adhesion to steel | | FINAT FTM 1 |
| 20 minutes (180°) N/25mm | 23 | |
| 24 hours (180°) N/25mm | 25 | |

RELEASE LINER

Structured lay-flat kraft paper liner, double-sided PE-coated

| | |
|----------------|-----|
| Thickness (µm) | 160 |
|----------------|-----|

PRODUCT APPLICATION

| | |
|------------------------------|----------|
| Application method | Dry |
| Application temperature (°C) | 10 to 30 |
| Service temperature (°C) | -5 to 50 |

DURABILITY

| | | |
|-----------------------------|----|--|
| Shelf life (months) | 12 | |
| Outdoor durability (months) | 3* | Northern-EU climate, vertical exposure |

*Lamination is recommended and can extend the outdoor durability of the film

ROLL SIZES

1220mm x 25m
1220mm x 50m

PRINTING METHOD

(Eco)-Solvent, Latex, UV

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in TITAN material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.